



KANKU INDUSTRIES

Mfg. : Chrome Pigment, Inorganics Pigment

ISO 9001:2008 CERTIFIED COMPANY

Primerose chrome KS 42

Technical Data Sheet

Section I-Information

Product	Primerose chrome
Colour Index Name	Pigment Yellow 34
Colour Index Number	77603

Section II-Physical Properties

Specific Gravity	(4-5)
Oil Absorption (MI/100Gm)	15-20
Moisture Content	Maximum 1.0%
Water Soluble Matter	Maximum 1.0%
Ph	(6-7)
Heat Stability	240*C-05 Minutes

Section III-Fastness Properties (1-5 Scale,1 Poor-5 Excellent)

Water	5	Xylene	(4-5)
Glycol	5	Minimum Temperature	5
Butanol	5	Mek	(4-5)
Acetone	5	Linseed Oil	5
Butyl Acetate	5	Soap	3
Light Fastness	Full Tone (0.2%) 6		
	Tint tone(1:10) 5-6		
Weather Fastness	Full Tone (0.2%)4-5		
	Tint tone (1:10) 3-4		

Section IV - Uses

Paint, Inks,Plastic, paint, coating, leather etc.

Mob. +91 99798 84643 (Mr. Kalp Patel)
Mob. +91 99798 89579 (Mr. Chetan Patel)

 kankuind@yahoo.in
kbp20in@yahoo.com
 www.kankuindustries.com

Plot No. 1206/15, 3rd Phase,G.I.D.C., VAPI-396 195.Dist. Valsad, Gujarat (INDIA)